

# SMOOTH HDPE GEOMEMBRANE

## ENGLISH UNITS

### Minimum Average Values

Property	Test Method	30 mil	40 mil	60 mil	80 mil	100 mil
Thickness, mils minimum average lowest individual reading	ASTM D 5199	30 27	40 36	60 54	80 72	100 90
Sheet Density, g/cc	ASTM D 1505/D 792	0.940	0.940	0.940	0.940	0.940
<b>Tensile Properties<sup>1</sup></b>	ASTM D 6693					
1. Yield Strength, lb/in		63	84	126	168	210
2. Break Strength, lb/in		114	152	228	304	380
3. Yield Elongation, %		12	12	12	12	12
4. Break Elongation, %		700	700	700	700	700
Tear Resistance, lb	ASTM D 1004	21	28	42	56	70
Puncture Resistance, lb	ASTM D 4833	54	72	108	144	180
Stress Crack Resistance <sup>2</sup> , hrs	ASTM D 5397 (App.)	300	300	300	300	300
Carbon Black Content <sup>3</sup> , %	ASTM D 1603	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596	--Note 4--				
Oxidative Induction Time (OIT) Standard OIT, minutes	ASTM D 3895	100	100	100	100	100
Oven Aging at 85°C High Pressure OIT - % retained after 90 days	ASTM D 5721 ASTM D 5885	80	80	80	80	80
UV Resistance <sup>5</sup> High Pressure OIT <sup>6</sup> - % retained after 1600 hrs	ASTM D 7238 ASTM D 5885	50	50	50	50	50
<b>Roll Dimensions</b>						
1. Width (feet):		23	23	23	23	23
2. Length (feet)		1000	750	500	375	300
3. Area (square feet):		23,000	17,250	11,500	8,625	6,900
4. Gross weight (pounds, approx.)		3,470	3,470	3,470	3,470	3,470

- 1 Machine direction (MD) and cross machine direction (XMD) average values should be on the basis of 5 test specimens each direction. Yield elongation is calculated using a gauge length of 1.3 inches; Break elongation is calculated using a gauge length of 2.0 inches.
  - 2 The yield stress used to calculate the applied load for the SP-NCTL test should be the mean value via MQC testing.
  - 3 Other methods such as ASTM D 4218 or microwave methods are acceptable if an appropriate correlation can be established.
  - 4 Carbon black dispersion for 10 different views: Nine in Categories 1 and 2 with one allowed in Category 3.
  - 5 The condition of the test should be 20 hr. UV cycle at 75°C followed by 4 hr. condensation at 60°C.
  - 6 UV resistance is based on percent retained value regardless of the original HP-OIT value.
- These data are provided for informational purposes only and are not intended as a warranty or guarantee. Poly-America assumes no responsibility in connection with the use of these data. Suitability for a particular use shall be determined by and is the sole responsibility of the end user. These values are subject to change without notice. REV. 08/11