

TEXTURED LLDPE GEOMEMBRANE

ENGLISH UNITS

Property	Test Method	Minimum Average Values		
		40 Mil	60 Mil	80 Mil
Thickness, mils	ASTM D 5994			
minimum average		38	57	76
lowest individual of 8 of 10 readings		36	54	72
lowest individual of 10 readings		34	51	68
Asperity Height ¹ , mils	ASTM D 7466	10	10	10
Sheet Density, g/cc (max.)	ASTM D 1505/D 792	0.939	0.939	0.939
Tensile Properties²	ASTM D 6693			
1. Break Strength, lb/in		60	90	120
2. Break Elongation, %		250	250	250
2% Modulus, lb/in ² (max.)	ASTM D 5323	60,000	60,000	60,000
Tear Resistance, lb	ASTM D 1004	22	33	44
Puncture Resistance, lb	ASTM D 4833	44	66	88
Axi-Symetric Break Strain, %	ASTM D 5617	30	30	30
Carbon Black Content ³ , %	ASTM D 1603	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon Black Dispersion	ASTM D 5596		--Note 4--	
Oxidative Induction Time (OIT)				
Standard OIT, minutes	ASTM D 3895	100	100	100
Oven Aging at 85°C	ASTM D 5721			
High Pressure OIT - % retained after 90 days	ASTM D 5885	60	60	60
UV Resistance ⁵	ASTM D 7238			
High Pressure OIT ⁶ - % retained after 1600 hrs	ASTM D 5885	35	35	35
Roll Dimensions				
1. Width (feet):		23	23	23
2. Length (feet):		750	500	375
3. Area (square feet):		17,250	11,500	8,625
4. Gross weight (pounds, approx.):		3,465	3,465	3,435

1 Of 10 readings; 8 must be ≥ 7 mils and lowest individual reading must be ≥ 5 mils.

2 Machine direction (MD) and cross machine direction (XMD) average values should be on the basis of 5 test specimens each direction. Break elongation is calculated using a gauge length of 2.0 inches.

3 Other methods such as ASTM D 4218 or microwave methods are acceptable if an appropriate correlation can be established.

4 Carbon black dispersion for 10 different views: Nine in Categories 1 and 2 with one allowed in Category 3.

5 The condition of the test should be 20 hr. UV cycle at 75°C followed by 4 hr. condensation at 60°C.

6 UV resistance is based on percent retained value regardless of the original HP-OIT value.

These data are provided for informational purposes only and are not intended as a warranty or guarantee. Poly-America assumes no responsibility in connection with the use of these data. Suitability for a particular use shall be determined by and is the sole responsibility of the end user. These values are subject to change without notice. REV. 08/11